



Grand Cayman

Product Specifications:

General

Total Wt. - oz./sq. yd. (CFFA-700d)	20.0 ± 10%
Total Wt. - oz./lin. yd. (CFFA-700d)	30
Width (min.) - in. (CFFA-700a)	54
Gauge (mils)	43 ± 10%
Face Content	Vinyl

Backing

Construction	Terry Knit
Weight - oz./sq. yd.	3.7
Content	Polyester
Fiber Type	Filament

Adhesion (CFFA-3)

Pounds/Inches (min.)	Warp 4.0
	Fill 4.0

Tensile Strength (CFFA-17)

Pounds (min.)	Warp 85
	Fill 75

Trap Tear Strength (CFFA-16c)

Pounds (min.)	Warp 20
	Fill 27

Tack Strength (Stitch) (CFFA-14)

Pounds (min.)	Warp 35
	Fill 30

Performance Testing: meets or exceeds

Abrasion

Wyzenbeek, wire wscreen	60,000 cycles
Wyzenbeek, cotton duck	400,000 cycles

Blocking (CFFA-4)

No. 2 Max

W-Flex (CFFA-10)

25,000 cycles

Crock (CFFA-7)

20 cycles - no stain

UV (CFFA-2)

QUV	650 hours (outdoors)
-----	----------------------

Mildew Resistance - ASTM G-21

Pass

Cold Crack (CFFA-6a)

-20°F

Flame Retardancy

California Tech. Bulletin 117	Pass
NFPA 260	Pass
FMVSS-302	Pass
UFAC Fabric, Class 1	Pass
BIFMA, Class A	Pass

Miscellaneous:

Application

Exterior/Interior

Finish

PreFixx® Protective Finish



ALL OMNOVA PRODUCTS AND SERVICES ARE OFFERED AND SOLD SUBJECT TO THE OMNOVA STANDARD TERMS AND CONDITIONS OF SALE AGREEMENT SET FORTH AT WWW.OMNOVA.COM

NAUTOLEX and PREFIX are registered trademarks of OMNOVA Solutions Inc.

© 2012 OMNOVA Solutions Inc. QA#023-CP-180 Rev.2. April 2012